

AD-A140 205

METAL-CHELATE POLYMERS: STRUCTURAL/PROPERTY  
RELATIONSHIPS AS A FUNCTION O. (U) MASSACHUSETTS UNIV  
AMHERST DEPT OF CHEMISTRY R D ARCHER ET AL. MAR 84

1/1


UNCLASSIFIED

TR-5 N00014-81-K-0611

F/G 7/3

NL

													END DATE FILMED 6-84 DTIC



MICROCOPY RESOLUTION TEST CHART  
NATIONAL BUREAU OF STANDARDS-1963-A

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER 5	2. GOVT ACCESSION NO. AD-A140205	3. RECIPIENT CATALOG NUMBER 10
4. TITLE (and Subtitle) Metal-Chelate Polymers: Structural/Property Relationships As A Function of the Metal Ion		5. TYPE OF REPORT & PERIOD COVERED Technical Report, Interim
7. AUTHOR(s) Ronald D. Archer, Christopher J. Hardiman, Kong S. Kim, Edward R. Grandbois, and Madeline Goldstein		6. PERFORMING ORG. REPORT NUMBER
9. PERFORMING ORGANIZATION NAME AND ADDRESS Department of Chemistry University of Massachusetts Amherst, MA 01003		8. CONTRACT OR GRANT NUMBER(s) N00014-81-K0611
11. CONTROLLING OFFICE NAME AND ADDRESS Office of Naval Research Department of the Navy Arlington, VA 22217		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS NR056-773
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		12. REPORT DATE March, 1984
		13. NUMBER OF PAGES 24
		15. SECURITY CLASS. (of this report) Unclassified
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Approved for Public Release, Distribution Unlimited		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report) This document has been approved for public release and sale; its distribution is unlimited		
18. SUPPLEMENTARY NOTES Accepted for publication in "Inorganic and Organometallic Polymers" to be published by Plenum Press.		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) bridging ligands 8,8'-dihydroxy-7,7'-dipropyl-5,5'-biquinolyl cadmium polymers lead polymers copper polymers metallated polymers film-forming metal chelate polymers 1,5-diazaanthraquinone nickel polymers (reverse side)		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) Polymers containing metal ions can exhibit properties quite different from the parent polymers from which they are derived. Metal ions added to pre-formed polymers can produce marked property changes, especially when the metal modifies the polymer backbone, as is the case in some of the polymeric hydrazones we have been investigating. When polymer syntheses are designed to place the metal ion directly in the backbone, even more pronounced differences are possible. Classically, planar arrays with conjugated ligands were used for thermal stability but they tend to produce intractability and yield		

DD FORM 1 JAN 73 1473

Unclassified

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

84 04 18 014

AD A140205

DTIC FILE COPY

19. Key Words (continued)

poly(terephthaloyloxalic-bis-amidrazone)  
poly (terephthaloylbutane-2,3-dihydrazone)  
thermal stability  
uranyl polymers  
zinc polymers

20 Abstract (continued)

only low molecular weight species. We are evaluating several methods which can minimize such intractability, including: ~~1)~~ ~~oxo~~ metal ions, such as uranyl(VI); ~~2)~~ bulky ligands, such as alkyl substituted ligands; and ~~3)~~ nonrigid eight-coordinate centers, such as tungsten(IV).

Unclassified

OFFICE OF NAVAL RESEARCH

Contract N00014-81-K-0611

Task No. NR 056-773

TECHNICAL REPORT NO. 5

METAL-CHELATE POLYMERS: STRUCTURAL/PROPERTY  
RELATIONSHIPS AS A FUNCTION OF THE METAL ION

by

Ronald D. Archer, Christopher J. Hardiman,  
Kong S. Kim, Edward R. Grandbois and Madeline Goldstein

Prepared for Publication

in

Inorganic and Organometallic Polymers  
Plenum Press

University of Massachusetts  
Department of Chemistry  
Amherst, MA 01003

March 1984

Accession No.	
100014-81-K-0611	
Task No. NR 056-773	
Contract No. N00014-81-K-0611	
Author(s) R. D. Archer, C. J. Hardiman, K. S. Kim, E. R. Grandbois, M. Goldstein	
Title METAL-CHELATE POLYMERS: STRUCTURAL/PROPERTY RELATIONSHIPS AS A FUNCTION OF THE METAL ION	
Institution UNIVERSITY OF MASSACHUSETTS	
Department DEPARTMENT OF CHEMISTRY	
Address AMHERST, MA 01003	
Date MARCH 1984	
Dist	
A-1	



Reproduction in whole or in part is permitted for  
any purpose of the United States Government

This document has been approved for public release  
and sale; its distribution is unlimited

METAL-CHELATE POLYMERS: STRUCTURAL/PROPERTY  
RELATIONSHIPS AS A FUNCTION OF THE METAL ION

Ronald D. Archer, Christopher J. Hardiman, Kong S. Kim,\*  
Edward R. Grandbois and Madeline Goldstein

Department of Chemistry and  
Materials Research Laboratory  
University of Massachusetts  
Amherst, MA 01003

INTRODUCTION

Metal ions chelated to preformed polymers can produce marked property changes, especially when the metal ion is bonded directly to the polymer backbone. Such metal-chelate polymers can show superior properties over their organic counterparts in certain applications,<sup>1</sup> although properties such as thermal stability are quite polymer and metal ion dependent.<sup>2</sup> A good example of improved thermal stability is provided by the zinc chelate of PTO; i.e., poly(terephthaloyloxalic-bis-amidrazone).<sup>3,4</sup> This metal-chelate polymer and many others are also good fire retardants. The existence of polymer-anchored metal catalysts is well documented, too.<sup>1,5-11</sup> However, superiority is not always the case. Brittleness and intractability are two properties often associated with metal-

\*Permanent address: Graduate School, Chungbuk University, Cheong-ju City, Korea. All work done at the University of Massachusetts.

containing polymers.<sup>12</sup> We are attempting to modify polymers through metal ion chelation and to vary the metal ions therein, in order to learn more about how such chelation modifies the properties of the polymers. The polymeric hydrazones under investigation in our laboratory provide examples of the changes which are possible.

When the metal ion is a part of the backbone itself, even more drastic property changes are possible. However, intractibility is often very severe in such polymers. In order to overcome the intractibility problems, we are synthesizing ligands and polymers with

- 1) oxo metal ions,
- 2) bulky ligands, and/or
- 3) non-rigid coordination centers.

Our initial studies using the latter have already been published.<sup>13</sup> This paper notes our progress in obtaining oxo-metal ion polymers for film-forming applications. To date these studies have concentrated on uranyl polymers. Ligand syntheses related to the other two methods are also noted.

## EXPERIMENTAL

### Synthesis

Poly(terephthaloyloxalic-bis-amidrazone), PTO, was obtained commercially and poly(terephthaloylbutane-2,3-dihydrazone), PTBH, was synthesized from butane-2,3-dihydrazone and terephthaloyl chloride in dimethylacetamide with a triethylamine catalyst. Anal. Calcd for  $C_{12}H_{12}N_4O_2$ : C, 59.0; H, 4.9; N, 22.9. Calcd for

$C_{12}H_{12}N_4O_2 \cdot H_2O$ : C, 55.0; H, 5.3; N, 21.4. Found\*: C, 56.5; H, 5.1; N, 21.5. For GPC of product see Fig. 1. The butanedihydrazone was synthesized by slowly adding a methanolic solution of 2,3-butanedione (diacetyl) to 64% aqueous hydrazine. The model ligand dibenzoylbutane-2,3-dihydrazone was prepared from benzoyl chloride and butane-2,3-dihydrazone in an analogous manner.

The metallated chelate polymers of PTO and PTBH were synthesized for several metals from aqueous ammonia solutions of the metal salts and the respective polymer. For less labile metal ions, e.g., nickel(II), elevated temperature reactions under pressure were used to avoid the loss of ammonia and to obtain stoichiometric metal content. Although a few hours at room temperature suffices for metal ions as labile as zinc(II), longer time periods at 90° are necessary for nickel(II). Chelation with PTBH requires longer times as the polymer is not swelled by concentrated aqueous ammonia like PTO. See Table 1.

Bis(8-quinolinol) was prepared by modifications of a published procedure of Bratz and von Niementowski.<sup>14</sup> A warm (40°) solution of ferric sulfate (210 g [0.5 mol] in 1400 mL  $H_2O$ ) was added rapidly to a 40° solution of 8-quinolinol (70 g [0.5 mol] in 1400 mL  $H_2O$ ). After 15 min of stirring, a NaOH solution (75.6 g in 700 mL  $H_2O$ ) was added over a period of an hour. After standing overnight, the black pasty material was filtered and dried. The paste was dissolved in 240 mL conc HCl and 320 mL glacial acetic acid via vigorous stirring and

\*Elemental analyses by the University of Massachusetts Microanalysis Laboratory.



Table 1. PTO and PTBH Metal Chelate Polymers<sup>a</sup>

Polymer	Metal Ion <sup>b</sup>	Temp.	Time	[NH <sub>3</sub> ]	Satn <sup>c</sup>
PTO	Zn <sup>++</sup>	25°	1 da	6 M	100 %
		25°	1 da	15 M	100 %
		90°	2 hr	15 M	100 %
PTO	Ni <sup>++</sup>	25°	2 da	6 M	80 %
		90°	2 hr	15 M	80 %
		90°	2 da	15 M	100 %
PTO	Cu <sup>++</sup>	25°	4 da	15 M	100 %
PTO	Cd <sup>++</sup>	25°	3 da	15 M	100 %
PTO	Pb <sup>++</sup>	25°	3 da	15 M	75 %
PTBH	Zn <sup>++</sup>	25°	1 da	15 M	70 %
		90°	2 da	15 M	100 %
PTBH	Ni <sup>++</sup>	90°	3 da	15 M	95 %
PTBH	Cu <sup>++</sup>	90°	3 da	15 M	55 %
PTBH	Cd <sup>++</sup>	90°	3 da	15 M	75 %
PTBH	Pb <sup>++</sup>	90°	3 da	15 M	100 %

<sup>a</sup>PTO = poly(terephthaloyloxalic-bis-amidrazone);

PTBH = poly(terephthaloylbutane-2,3-dihydrazone).


<sup>b</sup>Metal ions in 5 to 10 fold excess during reactions.<sup>c</sup>Satn = % saturation for 1 metal ion/polymer unit.

Fig. 1. GPC of PTBH vs polystyrene standards in NMP on Ultrastayragel

heating. Acetone (6.4 L) was used to precipitate the bright yellow dihydrochloride salt; yield, 22%. Addition of conc. aqueous ammonia to pH = 8 was followed by 1 hour stirring, filtering, washing with water, and drying in vacuo. Two recrystallizations from dimethylformamide, dissolution in HCl/H<sub>2</sub>O and reprecipitation with conc. aqueous ammonia as before provided a yield of 12%. Anal. Calcd for C<sub>18</sub>H<sub>12</sub>N<sub>2</sub>O<sub>2</sub>: C, 75.0; H, 4.2; N, 9.7. Found: C, 74.7; H, 4.2; N, 9.8.

Bis(7-propyl-8-quinolinol) was prepared by treating 7-allyl-8-quinolinol<sup>15</sup> with two equivalents of *p*-toluenesulfonylhydrazide<sup>16</sup> in diglyme under reflux conditions, precipitated with water, dissolved in CH<sub>2</sub>Cl<sub>2</sub>, concentrated, ether added and HCl salt precipitated with HCl gas. The salt was dissolved in water, neutralized to pH = 7.6, extracted with ether, dried with Na<sub>2</sub>SO<sub>4</sub>, concentrated to dryness at room temperature, and distilled (126°/5 mm Hg). The alkyl quinolinol was obtained in a 73% yield and was oxidatively coupled by adding an ethanolic solution to a basic aqueous solution of K<sub>3</sub>Fe(CN)<sub>6</sub>. The coupled product, alternatively designated as 8,8'-dihydroxy-7,7'-dipropyl-5,5'-biquinolyl, was obtained in a 21% yield after recrystallization from dimethylformamide. Anal. Calcd for C<sub>24</sub>H<sub>24</sub>N<sub>2</sub>O<sub>2</sub>: C, 77.4; H, 6.4; N, 7.5. Found: C, 76.8; H, 5.8; N, 7.5.

1,5-Diazaanthraquinone has been prepared through a simplified synthesis of a 1,5-diazaanthracene derivative. First, 2,6-dimethyl-1,2,3,4-tetrahydro-1,5-diazaanthracene-2,4,8-tricarboxylic acid was prepared from *p*-phenylenediamine and pyruvic acid according to the procedure of Giuliano and Stein;<sup>17</sup> yield, 39%. This compound was simultaneously decarboxylated and dehydrogenated with palladium on

charcoal in 1,2,4-trichlorobenzene under reflux for three hours. The crude 2,6-dimethyl-1,5-diazaanthracene was heated with concentrated nitric acid for seven hours. Upon cooling, 1,5-diazaanthraquinone-2,6-di-carboxylic acid crystallized as the dihydrate, yield, 14%. After removing the water of hydration, this diacid was decarboxylated by mixing it with twice its weight of calcium oxide and then heating the mixture rapidly in an evacuated sublimator. After one crystallization of the sublimate, 1,5-diazaanthraquinone was obtained as yellow/brown flakes; yield 15%, net yield overall, 1%. Anal. Calcd. for  $C_{12}H_6N_2O_2$ : C, 68.6; H, 2.9; N, 13.3. Found: C, 68.2; H, 3.0; N, 13.2.

Uranyl polymers have been synthesized through solution reactions as follows: A donor solvent such as dimethyl sulfoxide (DMSO) was used to dissolve stoichiometric quantities of a bridging ligand and uranyl acetate dihydrate. Typically, 100 mL of DMSO is sufficient for a one gram reaction. The DMSO/acetic acid azeotrope was distilled from the solution in vacuo using a minimum amount of heat and then taken to dryness. The progress of the reaction was monitored via NMR examination of the distillate. Drying the product overnight at 100° in vacuo typically gave analyses consistent with one to two moles DMSO per mole of the uranyl cation. See Table 2.

Uranyl polymers have also been synthesized interfacially based on the work of Carraher and Schroeder.<sup>18</sup> Initially, 0.02 mol of an appropriate bridging ligand, such as a dicarboxylic acid, was added to 100 mL of water, neutralized with a quantitative amount of NaOH, and placed in a high-speed blender. A solution of 0.02 mol uranyl

Table 2. Uranyl Polymers of Dicarboxylic Acids

Ligand	M <sub>n</sub> <sup>a</sup>	Empirical Formula/Analyses
2,2-Dimethylsuccinate <sup>b</sup>		UO <sub>2</sub> [O <sub>2</sub> CC(CH <sub>3</sub> ) <sub>2</sub> CH <sub>2</sub> CO <sub>2</sub> ](C <sub>2</sub> H <sub>5</sub> SO)
	7,000	Calcd: C, 19.5; H, 2.9; S, 6.5; U, 48.4 Found: C, 19.6; H, 2.9; S, 6.6; U, 48.3
2,2-Dimethylglutarate		UO <sub>2</sub> [O <sub>2</sub> CC(CH <sub>3</sub> ) <sub>2</sub> CH <sub>2</sub> CH <sub>2</sub> CO <sub>2</sub> ](C <sub>2</sub> H <sub>5</sub> SO)
	30,000	Calcd: C, 21.4; H, 3.2; S, 6.3; U, 47.0 Found: C, 21.4; H, 3.2; S, 6.9; U, 46.1
3,3-Dimethylglutarate		UO <sub>2</sub> [O <sub>2</sub> CCH <sub>2</sub> C(CH <sub>3</sub> ) <sub>2</sub> CH <sub>2</sub> CO <sub>2</sub> ](C <sub>2</sub> H <sub>5</sub> SO)
	10,000	Calcd: C, 21.4; H, 3.2; S, 6.3; U, 47.0 Found: C, 21.1; H, 3.2; S, 6.7; U, 47.1
2,2,6,6-Tetramethylpimelate <sup>c</sup>		UO <sub>2</sub> [O <sub>2</sub> C(CH <sub>3</sub> ) <sub>2</sub> (CH <sub>2</sub> ) <sub>3</sub> C(CH <sub>3</sub> ) <sub>2</sub> CO <sub>2</sub> ](C <sub>2</sub> H <sub>5</sub> SO)
	6,000	Calcd: C, 27.8; H, 4.3; S, 5.7; U, 42.3 Found: C, 27.8; H, 4.3; S, 5.6; U, 42.5
Thiodiglycolate		UO <sub>2</sub> (O <sub>2</sub> CCH <sub>2</sub> SCCH <sub>2</sub> CO <sub>2</sub> )(C <sub>2</sub> H <sub>5</sub> SO)
	4,000	Calcd: C, 15.7; H, 2.5; S, 15.0 Found: C, 16.0; H, 2.6; S, 15.1
Maleate		UO <sub>2</sub> (cis-O <sub>2</sub> CCH=CHCO <sub>2</sub> )(C <sub>2</sub> H <sub>5</sub> SO)
	8,000	Calcd: C, 17.3; H, 2.3; S, 10.8; U, 45.8 Found: C, 17.5; H, 2.5; S, 10.5; U, 45.4
Fumarate		UO <sub>2</sub> (trans-O <sub>2</sub> CCH=CHCO <sub>2</sub> )(C <sub>2</sub> H <sub>5</sub> SO)
	10,000	Calcd: C, 17.8; H, 2.6; S, 11.9; U, 44.1 Found: C, 17.8; H, 2.6; S, 11.5; U, 43.8
Phthalate		UO <sub>2</sub> (o-O <sub>2</sub> CC <sub>6</sub> H <sub>4</sub> CO <sub>2</sub> )(C <sub>2</sub> H <sub>5</sub> SO)
	10,000	Calcd: C, 24.4; H, 2.7; S, 10.9; U, 40.3 Found: C, 24.3; H, 2.8; S, 10.6; U, 40.5
Isophthalate		UO <sub>2</sub> (m-O <sub>2</sub> CC <sub>6</sub> H <sub>4</sub> CO <sub>2</sub> )(C <sub>2</sub> H <sub>5</sub> SO)
	lim solb	Calcd: C, 23.7; H, 2.2; S, 7.5; U, 44.8 Found: C, 23.8; H, 2.0; S, 7.6; U, 44.9
Terephthalate		UO <sub>2</sub> (p-O <sub>2</sub> CC <sub>6</sub> H <sub>4</sub> CO <sub>2</sub> )(C <sub>2</sub> H <sub>5</sub> SO)
	insolb	Calcd: C, 24.4; H, 2.7; S, 10.9; U, 40.3 Found: C, 24.2; H, 2.7; S, 10.9; U, 40.2
Acetylenedicarboxylate		UO <sub>2</sub> (O <sub>2</sub> CC≡CCO <sub>2</sub> )(C <sub>5</sub> H <sub>9</sub> NO)
	6,000	Calcd: C, 27.6; H, 2.9; N, 4.4; U, 42.8 Found: C, 26.9; H, 3.5; N, 4.6; U, 44.4

<sup>a-c</sup>Footnotes at the top of the next page

Table 2. (continued)

<sup>a</sup>  $M_n$  values based on GPC & viscosity in NMP relative to polystyrene.

<sup>b</sup> The uranyl polymer of dimethylsuccinate was also synthesized in pyridine (the monopyridine product requires N, 2.8; found: N, 2.5) and interfacially (the diaqua product requires C, 16.0; H, 2.7; found: C, 15.8; H, 2.1).

<sup>c</sup> The uranyl polymer of tetramethylpimelate was also synthesized in pyridine (the monopyridine product requires N, 2.5; found: N, 2.4) (the diaqua product requires C, 25.4; H, 4.3; found: C, 25.8; H, 3.9).




Fig. 2. GPC spectra (in NMP on  $10^3$  Å Ultrastyrigel) of  $\text{UO}_2(2,2\text{-dimethylsuccinate}) \cdot 2\text{H}_2\text{O}$  polymer isolated during an interfacial polymerization. The Upper curve is the precipitate formed at the interface during the polymerization ( $M_n$  ca. 25,000 vs. polystyrene). The dotted line represents an estimate for the polymer which exceeds the exclusion limit of the column. The Lower curve represents the precipitate which occurs from the aqueous layer upon cooling ( $M_n$  ca. 7,000 vs. polystyrene).

nitrate hexa- hydrate in diethyl ether was also placed in the blender and the two phase system was mixed at high velocity for 30 seconds and the product was filtered from the solution. Drying overnight at 100° in vacuo typically provided analyses consistent with diaquo species.

### Properties

Standard methods were used for all studies. Of particular note are the gel permeation studies of the uranyl polymers. Since they are generally insoluble in tetrahydrofuran, the usual solvent of choice, the polymers could not be easily studied until the recent availability of columns compatible with N-methyl-2-pyrrolidone (NMP) (Ultrastyrigel/Waters).

## RESULTS AND DISCUSSION

### PTO and PTBH Polymers


Metallated PTO polymers show that extreme differences in behavior which can result from the direct attachment of metal ions directly onto a polymeric backbone. Whereas the zinc derivative is appreciably more thermally stable than the parent polymer,<sup>2,3</sup> we find that the nickel(II) and copper(II) derivatives are less thermally stable than the parent polymer. See Table 3. This modification thermal stability is dependent on saturation of the polymer by the metal ion; e.g., Frank and coworkers<sup>19</sup> have claimed no enhanced stability for the zinc PTO derivative, in direct opposition to the results of van Krevelen<sup>2</sup> and ourselves. Similarly, the mechanical properties of the zinc PTO derivative are excellent, but the nickel-

Table 3. Decomposition Temperatures for PTO and PTBH Metal Polymers

Polymer	Metal-free	Zn(II)	Ni(II)	Cu(II)	Cd(II)	Pb(II)
PTO	325°C	500°	300°	300°	450°	unsatd
PTBH	290°C	350°	330°	unsatd	unsatd	340°


<sup>a</sup>unsatd = unsaturated.

(II) derivative is very brittle after annealing at 100° for the normal drying period of several hours. One potential bonding mode for the zinc PTO derivative is shown in structure 1.



Note that the coordination of zinc to four of the donor atoms leaves four other nitrogen donors free as potential crosslinking sites. Our choice of 1 as the mode of coordination is based on the loss of carbonyl stretching transitions in the infrared upon coordination of zinc, and the other metal ions as well. The mode of coordination had been in dispute previously,<sup>2,3,19,20</sup> although Frank *et al.*<sup>19</sup> had come to a similar conclusion. The electronic spectra of the metallate PTO species show large bathochromic (red) shifts as expected for a more conjugated system. The parent polymer backbone

of PTO ,2, lacks total conjugation.



2

The brittleness of nickel(II) derivative coupled with the knowledge that nickel(II) is often six-coordinate led us to synthesize the PTBH polymer, in which the amine groups in 1 are replaced with methyl groups. We felt that this substitution should minimize the crosslinking possibilities for the nickel ions. To our surprise, the nickel(II) derivative is once again appreciably less stable than the analogous zinc derivative. The stability of the nickel derivative relative to the parent polymer appears to be dependent on the stoichiometry of the product. Again the copper(II) derivative is similar in stability to the nickel species. Cadmium and lead derivatives, even when not fully stoichiometric, are better than the transition elements. Together these results suggest the rigid stereochemistry of the partially filled d level ions (tetragonal planar for four coordination for these types of ligands) causes the rigidity. The d<sup>10</sup> ions have no favored angles (although ligand donor donor atom repulsions favor movement toward a tetrahedron). The lower thermal stability was unexpected, but as noted by Carraher,<sup>18</sup> each system of chelated polymeric materials appears different.




### Bridging Ligands

Conjugated bridging ligands have been synthesized in order to prepare thermally stable metal chelate polymers which might show electron transport properties. 5,5'-Bis(8-quinolinol) is difficult to obtain pure. The coupling reaction involves iron(III), which stays coordinated except in strongly acidic or basic media. Unfortunately, after being purified by sequential treatment with acid and then base, the product exhibited low solubility and was difficult to use in polymer synthesis. However, it is known that alkyl substitution often increases the solubility of 8-quinolinol derivatives quite markedly, and 5,5'-bis(7-propyl-8-quinolinol) is no exception. Its solubility is much greater than the non-alkyl substituted species. Although we had hoped to oxidize these to quinone forms so we could oxidize and polymerize tungsten(II) precursors as we had done with quinoxaline-5,8-dione,<sup>13</sup> such oxidations have been unsuccessful to date. An alternative ligand, 1,5-diaza-anthra-9,10-quinone, has been synthesized for analogous purposes. The synthesis is much improved over the literature procedure for its precursor, 1,5-diazaanthracene.<sup>21</sup> The earlier procedure has several more steps and an even poorer yield. The reaction of the quinone with  $W(CO)_3-(PPh_3)_2Cl_2$  is negligible thermally, but photochemical activation allows some product formation, although the details have not been worked out as yet. Thus, although the oxidizing ability of diaza-anthraquinone is appreciably less than that of quinoxalinedione, photochemical activation may allow its use in successful polymer synthesis.

### Uranyl Polymers


Polymeric species with the metal ions directly in the backbone can alter the polymer properties significantly, even when cross-linking is not taking place. To minimize chain stacking forces, we are using the dioxouranate(VI) ion. We have synthesized a wide variety of amorphous, film-forming, uranyl dicarboxylate polymers. On the other hand, Beilstein<sup>22</sup> lists a large number of metal derivatives of 2,2-dimethylsuccinic acid, maleic acid, and fumaric acid as crystalline. Although fewer derivatives of the other acids have been listed,<sup>23</sup> in general, the metal ion derivatives of the dicarboxylates have been isolated as micro-crystalline species. Our success in producing non-crystalline polymers may be related to the careful control of stoichiometry in the solution polymerizations of the diacids with uranyl acetate (equation 1) in polar solvents.



The acetic acid is removed in vacuo to drive reaction 1 to the right. Although we have had some success in pyridine, DMSO appears to be the solvent of choice in most cases. The sulfur analysis provides unambiguous evidence for the degree of solvation in the products. Pyridine can be similarly analyzed for nitrogen, but the lower solubilities of the polymers in pyridine causes precipitation before adequate chain lengths had been obtained. The amorphous nature of the products is probably aided by the dioxouranate(VI) ion, which interacts strongly with the carboxylates, and even cross-

links in the absence of coordinating solvents, but has enough bulk to minimize chain interactions. The number-average molecular weights of the uranyl polymers relative to polystyrene range from 4000 to 30,000, consistent with expectations for step-growth condensation polymerizations which are stoichiometrically limited. Ligand purity varied from acid to acid, and the thiodiglycolic was the poorest in quality.

Interfacial polymerizations, as in equation 2, have also been used, where the uranyl nitrate, dissolved in diethyl ether, and the disodium salt of the diacid, dissolved in water, were stirred together at high speeds for up to 30 seconds.



The procedure is analogous to that used by Carraher and Schroeder.<sup>18</sup> Molecular weight improvement occurred by interfacial synthetic procedures for 2,2-dimethylsuccinate. However, the lower solubility of the product and the necessity of finding the proper concentration conditions for enhanced molecular weights, not necessarily stoichiometric, caused us to continue with solution polymerizations for most of our studies.

Infrared spectra are consistent with coordinated carboxylate with very weak bands due to uncoordinated carbonate occasionally observed at intensities low enough to suggest that the molecular weight estimates are real. In other samples weak methyl NMR signals suggest acetate end groups.

These yellow polymers display good glass adhesion and are being evaluated for radiation sensitivity for lithography. Preliminary results are very encouraging.

### Conclusion

Overall, the prospects for significant improvements in polymers through the appropriate incorporation of metal ions is evident. The properties of such polymers are very metal-ion dependent. Minor changes in metal ion content can also make significant differences in the resulting properties of the polymeric materials produced. Modification of the coordination sphere of a given metal provides another pathway to property modification that remains to be explored.

### Acknowledgment

The authors gratefully acknowledge the support of the Office of Naval Research and the National Science Foundation Materials Research Laboratory program for support of this research.

### REFERENCES

1. J. E. Sheats, Kirk-Othmer Ency. Chem. Tech., 3rd ed., 15, 184 (1981).
2. C. E. Carraher, Jr., J. Macromol. Sci.-Chem. A17, 1293 (1982).
3. D. W. van Krevelen, Chem. and Ind., 49, 1396 (1971); Angew. makromol. Chem., 22, 133 (1972).
4. Anon., Textile Progr., 8, 124, 156 (1976).

5. C. U. Pittman, Jr., "Polymer-Supported Reactions in Organic Synthesis (P. Hodge and D. C. Sherrington, Eds.), Wiley, New York, 1980, Chpt.5.
6. C. Carlini and G. Sbrana, J. Macromol. Sci.-Chem., A16, 323 (1981).
7. D. W. Slocum, B. Conway, M. Hodgman, K. Kuchel, M. Moronski, R. Nobel, K. Webber, S. Duraj, A. Siegel, and D. A. Owen, J. Macromol. Sci.-Chem., A16, 357, (1981).
8. Y. Chauvin, D. Commereuc and F. Dawans, Progr. Polym. Sci., 5, 95 (1977).
9. J. P. Collman and L. S. Hegedus, "Principles and Applications of Organotransition Metal Chemistry," University Science Books, Mill Valley, CA, 1980, p. 370.
10. F. R. Hartley and P. N. Vezey, Adv. Organomet. Chem., 15, 189 (1977).
11. J. C. Bailar, Jr., Catal. Rev.-Sci. Eng. 10, 17, (1974).
12. J. C. Bailar, Jr., "Organometallic Polymers" (C. E. Carraher, Jr., J. E. Sheats, and C. U. Pittman, Jr., Eds.) Academic Press, N. Y., 1978, p. 313.
13. R. D. Archer, W. H. Batschelet and M. L. Illingsworth, J. Macromol. Sci.-Chem., A16, 261 (1981).
14. L. T. Bratz and S. von Niementowski, Ber., 52B, 189 (1919).
15. B. Mander-Jones and V. M. Trikojus, J. Proc. Roy. Soc. N. S. Wales, 66, 300 (1932).

16. R. S. Dewey and E. E. vanTamelin, J. Am. Chem. Soc., 83, 3729 (1961).
17. R. Giuliano and M. L. Stein, Gazz. Chim. Ital., 84, 284 (1954).
18. C. E. Carraher, Jr. and J. A. Schroeder, J. Polym. Sci. Polym. Lett. Ed., 13, 215 (1975).
19. V. D. Frank, W. Dietrich, J. Dehnke, A. Kobock, G. Schuch and M. Wallrahe, Angew. Makromol. Chem., 40, 445 (1974).
20. D. W. van Krevelen, Chem. Eng. Tech., 47, 793 (1975).
21. P. Ruggli and E. Preiswerk, Helv. Chem. Acta, 22, 478 (1939).
22. Beilstein, II, 662, 740, 751 (and analogous pages in suppl. 1 - 4).
23. Beilstein, II, 677, 684, 728, 802 (and analogous pages in suppl. 1 - 4).

DL/413/83/01  
GEN/413-2

TECHNICAL REPORT DISTRIBUTION LIST, GEN

	<u>No. Copies</u>		<u>No. Copies</u>
Office of Naval Research Attn: Code 413 800 N. Quincy Street Arlington, Virginia 22217	2	Naval Ocean Systems Center Attn: Technical Library San Diego, California 92152	1
ONR Pasadena Detachment Attn: Dr. R. J. Marcus 1030 East Green Street Pasadena, California 91106	1	Naval Weapons Center Attn: Dr. A. B. Amster Chemistry Division China Lake, California 93555	1
Commander, Naval Air Systems Command Attn: Code 310C (H. Rosenwasser) Washington, D.C. 20360	1	Scientific Advisor Commandant of the Marine Corps Code RD-1 Washington, D.C. 20380	1
Naval Civil Engineering Laboratory Attn: Dr. R. W. Drisko Port Hueneme, California 93401	1	Dean William Tolles Naval Postgraduate School Monterey, California 93940	1
Superintendent Chemistry Division, Code 6100 Naval Research Laboratory Washington, D.C. 20375	1	U.S. Army Research Office Attn: CRD-AA-IP P.O. Box 12211 Research Triangle Park, NC 27709	1
Defense Technical Information Center Building 5, Cameron Station Alexandria, Virginia 22314	12	Mr. Vincent Schaper DTNSRDC Code 2830 Annapolis, Maryland 21402	1
DTNSRDC Attn: Dr. G. Bosmajian Applied Chemistry Division Annapolis, Maryland 21401	1	Mr. John Boyle Materials Branch Naval Ship Engineering Center Philadelphia, Pennsylvania 19112	1
Naval Ocean Systems Center Attn: Dr. S. Yamamoto Marine Sciences Division San Diego, California 91232	1	Mr. A. M. Anzalone Administrative Librarian PLASTEC/ARRADCOM Bldg 3401 Dover, New Jersey 07801	1

TECHNICAL REPORT DISTRIBUTION LIST, 056

Dr. G. A. Somorjai  
Department of Chemistry  
University of California  
Berkeley, California 94720

Dr. J. Murday  
Naval Research Laboratory  
Surface Chemistry Division (6170)  
455 Overlook Avenue, S.W.  
Washington, D.C. 20375

Dr. J. B. Hudson  
Materials Division  
Rensselaer Polytechnic Institute  
Troy, New York 12181

Dr. Theodore E. Madey  
Surface Chemistry Section  
Department of Commerce  
National Bureau of Standards  
Washington, D.C. 20234

Dr. Chia-wei Woo  
Department of Physics  
Northwestern University  
Evanston, Illinois 60201

Dr. Robert M. Hexter  
Department of Chemistry  
University of Minnesota  
Minneapolis, Minnesota

Dr. J. E. Demuth  
IBM Corporation  
Thomas J. Watson Research Center  
P.O. Box 218  
Yorktown Heights, New York 10598

Dr. M. G. Lagally  
Department of Metallurgical  
and Mining Engineering  
University of Wisconsin  
Madison, Wisconsin 53706

Dr. Adolph B. Amster  
Chemistry Division  
Naval Weapons Center  
China Lake, California 93555

Dr. W. Kohn  
Department of Physics  
University of California, San Diego  
La Jolla, California 92037

Dr. R. L. Park  
Director, Center of Materials  
Research  
University of Maryland  
College Park, Maryland 20742

Dr. W. T. Peria  
Electrical Engineering Department  
University of Minnesota  
Minneapolis, Minnesota 55455

Dr. Keith H. Johnson  
Department of Metallurgy and  
Materials Science  
Massachusetts Institute of Technology  
Cambridge, Massachusetts 02139

Dr. J. M. White  
Department of Chemistry  
University of Texas  
Austin, Texas 78712

Dr. R. P. Van Duyne  
Chemistry Department  
Northwestern University  
Evanston, Illinois 60201

Dr. S. Sibener  
Department of Chemistry  
James Franck Institute  
5640 Ellis Avenue  
Chicago, Illinois 60637

Dr. Arold Green  
Quantum Surface Dynamics Branch  
Code 3817  
Naval Weapons Center  
China Lake, California 93555

Dr. S. L. Bernasek  
Princeton University  
Department of Chemistry  
Princeton, New Jersey 08544



TECHNICAL REPORT DISTRIBUTION LIST, 056

Dr. F. Carter  
Code 6132  
Naval Research Laboratory  
Washington, D.C. 20375

Dr. Richard Colton  
Code 6112  
Naval Research Laboratory  
Washington, D.C. 20375

Dr. Dan Pierce  
National Bureau of Standards  
Optical Physics Division  
Washington, D.C. 20234

Professor R. Stanley Williams  
Department of Chemistry  
University of California  
Los Angeles, California 90024

Dr. R. P. Messmer  
Materials Characterization Lab.  
General Electric Company  
Schenectady, New York 22217

Dr. Robert Gomer  
Department of Chemistry  
James Franck Institute  
5640 Ellis Avenue  
Chicago, Illinois 60637

Dr. Ronald Lee  
R301  
Naval Surface Weapons Center  
White Oak  
Silver Spring, Maryland 20910

Dr. Paul Schoen  
Code 5570  
Naval Research Laboratory  
Washington, D.C. 20375

Dr. John T. Yates  
Department of Chemistry  
University of Pittsburgh  
Pittsburgh, Pennsylvania 15260

Dr. Richard Greene  
Code 5230  
Naval Research Laboratory  
Washington, D.C. 20375

Dr. L. Kesmodel  
Department of Physics  
Indiana University  
Bloomington, Indiana 47403

Dr. K. C. Janda  
California Institute of Technology  
Division of Chemistry and Chemical  
Engineering  
Pasadena, California 91125

Professor E. A. Irene  
Department of Chemistry  
University of North Carolina  
Chapel Hill, North Carolina 27514

Dr. Adam Heller  
Bell Laboratories  
Murray Hill, New Jersey 07974

Dr. Martin Fleischmann  
Department of Chemistry  
Southampton University  
Southampton SO9 5NH  
Hampshire, England

Dr. John W. Wilkins  
Cornell University  
Laboratory of Atomic and  
Solid State Physics  
Ithaca, New York 14853

Dr. Richard Smardzewski  
Code 6130  
Naval Research Laboratory  
Washington, D.C. 20375

Dr. H. Tachikawa  
Chemistry Department  
Jackson State University  
Jackson, Mississippi 39217

TECHNICAL REPORT DISTRIBUTION LIST, 056

Dr. R. G. Wallis  
Department of Physics  
University of California  
Irvine, California 92664

Dr. D. Ramaker  
Chemistry Department  
George Washington University  
Washington, D.C. 20052

Dr. P. Hansma  
Physics Department  
University of California  
Santa Barbara, California 93106

Dr. J. C. Hemminger  
Chemistry Department  
University of California  
Irvine, California 92717

Professor T. F. George  
Chemistry Department  
University of Rochester  
Rochester, New York 14627

Dr. G. Rubloff  
IBM  
Thomas J. Watson Research Center  
P.O. Box 218  
Yorktown Heights, New York 10598

Professor Horia Metiu  
Chemistry Department  
University of California  
Santa Barbara, California 93106

Captain Lee Myers  
AFOSR/NC  
Bolling AFB  
Washington, D.C. 20332

Professor Roald Hoffmann  
Department of Chemistry  
Cornell University  
Ithaca, New York 14853

Dr. R. W. Plummer  
Department of Physics  
University of Pennsylvania  
Philadelphia, Pennsylvania 19104

Dr. E. Yeager  
Department of Chemistry  
Case Western Reserve University  
Cleveland, Ohio 41106

Professor D. Hercules  
University Pittsburgh  
Chemistry Department  
Pittsburgh, Pennsylvania 15260

Professor N. Winograd  
Department of Chemistry  
Pennsylvania State University  
University Park, Pennsylvania 16802

Dr. G. D. Stein  
Mechanical Engineering Department  
Northwestern University  
Evanston, Illinois 60201

Professor A. Steckl  
Department of Electrical and  
Systems Engineering  
Kensselaer Polytechnic Institute  
Troy, New York 12181

Professor G. H. Morrison  
Department of Chemistry  
Cornell University  
Ithaca, New York 14853

Dr. David Squire  
Army Research Office  
P.O. Box 12211  
Research Triangle Park, NC 27709

Dr. R. D. Archer  
Chemistry Department  
University of Massachusetts  
Amherst, Massachusetts 01003

DL/413/83/01  
056/413-2

TECHNICAL REPORT DISTRIBUTION LIST, 056

Dr. J. E. Jensen  
Hughes Research Laboratory  
3011 Malibu Canyon Road  
Malibu, California 90265

Dr. J. H. Weaver  
Department of Chemical Engineering  
and Materials Science  
University of Minnesota  
Minneapolis, Minnesota 55455

Dr. W. Knauer  
Hughes Research Laboratory  
3011 Malibu Canyon Road  
Malibu, California 90265

Dr. C. B. Harris  
Department of Chemistry  
University of California  
Berkeley, California 94720

MED  
-8